

Typ pianki: CV 2533
Numer serii: 312
Data produkcji: 2017.02.11
Data badan: 2017.02.13

Metod badawcza:

Furniture and Furnishings (FIRE)(SAFETY) Regulations 1988,
Schedule 1 part 1 (amended 1989) based on BS 5852: 1982 Part 2 (crib5)

Rezultat

No.	Ignition / Non-Ignition	Duration	
		Ignition Source	Flames
1	PASS (N/I)	crib 5	2min 38sec
2	PASS (N/I)	crib 5	3min 05sec

Weight loss:	1st Application:	0.038 kg
	2nd Application:	0.045 kg.

Wynik Badan:	Zgodna z wymaganiami
--------------	-----------------------------

L.Biliuviene
Badane przez:

G.Ciceniene
Manager jakosci:

